

## **Product Data Sheet**

# **PUROLITE® PFA300**

**Strong Base Anion Gel** 

## Gel Type II Strong Base Anion Exchange Resin

Purofine PFA300 is a gel-type II strong base anion exchange resin which because of its special narrow size distribution has particularly high operating capacity at lower regeneration levels, where its superior regeneration efficiency is most marked. It is the resin of choice where the water to be treated contains a high proportion of mineral acids (as opposed to silica). It is also relatively less susceptible to organic fouling than are standard gel-type strong base anion resins. Consequently higher purity treated water (or other solution) can generally be obtained, and rinse volumes, and hence rinse times are considerably reduced. However normal care should be taken that the maximum temperature of operation and regeneration applicable to type II resins (given below) is not exceeded. The increased capacity which is available may be used to obtain longer runs and higher throughputs, which can also be realized where small or shallow resin beds are required. These significant advantages result from improved optimum rates of ion exchange loading and regeneration. Thus economies may be made both to operating and capital costs.

#### **Basic Features:**

Application Regeneration Efficient Demineralization - Uniformily Sized

Polymer Structure Gel polystyrene crosslinked with divinylbenzene

Appearance Spherical beads

Functional Group Type 2 Quaternary Ammonium

Ionic form as shipped CI

### **Typical Physical and Chemical Characteristics:**

Total Capacity (min.)	Cl	1.40 eq/l
Total Capacity (min.)	Cl	30.57 kGr/ft <sup>3</sup>
Moisture Retention	CI <sup>-</sup>	40-45 %
Mean Size Typical		0.52-0.62 mm
Uniformity Coefficient (max.)		1.20
Reversible Swelling (max.)	$Cl^{-} \rightarrow OH^{-}$	10 %
Specific Gravity		1.09 g/ml
Shipping Weight (approx.)		675-700 g/l
Shipping Weight (approx.)		42.2-43.8 lbs/ft <sup>3</sup>
Temp Limit	OH <sup>-</sup>	35 °C
Temp Limit	OH-	104 °F
Temp Limit	Cl	85 °C
Temp Limit	Cl	185 °F

Telephone: (1) 610-668-9090

Fax: (1) 610-668-8139

Email: info@puroliteusa.com

© 2007 All Rights Reserved

Europe

Telephone: +44 1443 229334

Fax: +44 1443 227073

Email: sales@purolite.com

Asia Pacific

Telephone: +86 571 876 31385

Fax: +86 571 876 31385

Email: pultalan@purolitechina.com



# **Product Data Sheet**

PUROLITE® PFA300

**Strong Base Anion Gel** 

pH Limits		0-14 (Stability)
pH Limits	OH <sup>-</sup>	1-10 (Operating)

USA

Telephone: (1) 610-668-9090 Fax: (1) 610-668-8139 Email: info@puroliteusa.com Europe

Telephone: +44 1443 229334 Fax: +44 1443 227073 Email: sales@purolite.com Asia Pacific

Telephone: +86 571 876 31385
Fax: +86 571 876 31385
Email: pultalan@purolitechina.com