

# **Product Data Sheet**

PUROLITE® PFC100H Strong Acid Cation Gel

Gel Type Strong Acid Cation Exchange Resin

PFC100H/4460 is a fine mesh gel type strong acid cation exchange resin with excellent resistance to both osmotic and thermal shock. Its special particle sizing permits higher rates of diffusion of most cations including those of heavy metals and amines and also positively charged organics of higher molecular weight, and facilitates their removal on regeneration. These properties of physical robustness, good regenerability, and fast kinetics of exchange make it ideal for a range of applications. In such cases, it is the general rule that a specially graded particle size is required. PFC100H/4460 has a specially tailored particle size for high efficiency make-up water softening, hydrometallurgy, heavy metal removal, sugar treatment, and demineralisation of numerous organic solutions to name but a few.

### **Basic Features:**

| Application           | Demineralization of Water - Uniform Particle Sized Beads |
|-----------------------|--|
| Polymer Structure     | Gel polystyrene crosslinked with divinylbenzene          |
| Appearance            | Spherical beads  |
| Functional Group      | Sulphonic acid   |
| lonic form as shipped | H <sup>+</sup>   |

## **Typical Physical and Chemical Characteristics:**

| Total Capacity (min.)         | Na <sup>+</sup>        | 2 eq/l                        |
|-------------------------------|------------------------|-------------------------------|
| Total Capacity (min.)         | Na <sup>+</sup>        | 43.67 kGr/ft <sup>3</sup>     |
| Moisture Retention            | H <sup>+</sup>         | 51-55 %                       |
| Mean Size Typical             |                        | 0.52-0.62 mm                  |
| Uniformity Coefficient (max.) |                        | 1.20                          |
| Reversible Swelling (max.)    | $Na^+ \rightarrow H^+$ | 8 %                           |
| Specific Gravity              |                        | 1.20 g/ml                     |
| Shipping Weight (approx.)     |                        | 745-770 g/l                   |
| Shipping Weight (approx.)     |                        | 46.6-48.1 lbs/ft <sup>3</sup> |
| Temp Limit                    | H <sup>+</sup>         | 120 °C                        |
| Temp Limit                    | H <sup>+</sup>         | 250 °F                        |
| Temp Limit                    | Na <sup>+</sup>        | 140 °C                        |
| Temp Limit                    | Na <sup>+</sup>        | 285 °F                        |
| pH Limits                     |                        | 0-14                          |

### USA

Telephone: (1) 610-668-9090 Fax: (1) 610-668-8139 Email: info@puroliteusa.com Europe Telephone: +44 1443 229334 Fax: +44 1443 227073 Email: sales@purolite.com

#### Asia Pacific

Telephone: +86 571 876 31385 Fax: +86 571 876 31385 Email: pultalan@purolitechina.com

www.purolite.com