

## **Product Data Sheet**

PUROLITE® PPC100
Strong Acid Cation Gel

Gel Type Strong Acid Cation Exchange Resin

Puropack PPC100 is a specially produced, premium narrow size grading, gel strong acid cation exchange resin. It is one of a range of Puropack products manufactured for use in modern day water treatment applications. Puropack PPC100 is especially recommended for use in all counterflow demineralization systems, including the Puropack system. It is produced using Purolite's proprietary direct manufacturing process (DMP) and which results in a highly uniform and tailored product which provides for economical regeneration by counterflow techniques. Puropack is a maximum performance packed bed system which provides a combination of superior engineering principles and improved resins that together optimize water treatment plant performance. For more information please refer to the Puropack Manual or your local Purolite Sales Office. The product is also available in the hydrogen form as Puropack PPC100H.

## **Basic Features:**

Application	Narrow graded version of C100 offering high capacity and low regenerant consumption	
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene	
Appearance	Spherical beads	
Functional Group	Sulphonic acid	
lonic form as shipped	Na <sup>+</sup>	

## **Typical Physical and Chemical Characteristics:**

Total Capacity (min.)	Na <sup>+</sup>	2 eq/l
Total Capacity (min.)	Na <sup>+</sup>	43.67 kGr/ft <sup>3</sup>
Moisture Retention	Na <sup>+</sup>	44-48 %
Mean Size Typical		0.60-0.70 mm
Uniformity Coefficient (max.)		1.20
Reversible Swelling (max.)	$Na^+ \rightarrow H^+$	8 %
Specific Gravity		1.29 g/ml
Shipping Weight (approx.)		805-830 g/l
Shipping Weight (approx.)		50.3-51.9 lbs/ft <sup>3</sup>
Temp Limit	H <sup>+</sup>	120 °C
Temp Limit	H <sup>+</sup>	250 °F
Temp Limit	Na <sup>+</sup>	140 °C
Temp Limit	Na <sup>+</sup>	285 °F
pH Limits		0-14

USA Telephone: (1) 610-668-9090 Fax: (1) 610-668-8139 Email: info@puroliteusa.com **Europe** Telephone: +44 1443 229334 Fax: +44 1443 227073 Email: sales@purolite.com

## Asia Pacific

Telephone: +86 571 876 31385 Fax: +86 571 876 31385 Email: pultalan@purolitechina.com